

<u>Compound</u>	<u>Recommended Applications</u>	<u>Recommended Temperature Range (°F)</u>	<u>Color</u>	<u>Comments</u>
FLUOROCARBON (FKM, FPM)				
General Purpose				
V0986-50	General Purpose	-15 to 400	BROWN	
V7083-50	General Purpose	-15 to 400	BEIGE	Contact for new business opportunities
V0763-60	General Purpose	-15 to 400	BROWN	
V0769-60	General Purpose, Semicon	-15 to 400	BLACK	
V7058-60	General Purpose	-15 to 400	BLACK	Contact for new business opportunities
VA150-65	General Purpose	-15 to 400	BLACK	Contact for new business opportunities
VW450-65	Automotive gaskets	-15 to 400	BLUE	Contact for new business opportunities
V0680-70	FDA, NSF 51, USP Class VI	-15 to 400	RED	
V7041-70	General Purpose	-15 to 400	BLACK	
VW490-70	Automotive gaskets	-15 to 400	GREEN	
V0747-75	AMS-R-83248, TY I, CL I, UL listed	-15 to 400	BLACK	
V0848-75	Internally Lubed (PTFE powder)	-15 to 400	BLACK	
V1436-75	General Purpose, UL Listed	-15 to 400	BLACK	
V1475-75	General Purpose	-15 to 400	BLACK	
V1476-75	General Purpose	-15 to 400	BROWN	
VA075-75	General Purpose, UL Listed, alternate for V0747/V1164/VM330	-15 to 400	BLACK	
VA151-75	General Purpose, UL Listed	-15 to 400	BLACK	
VA169-75	Low Compression Set	-15 to 400	BLACK	
VA179-75	High temperature, Turbo applications	-10 to 437	BLACK	Contact for new business opportunities
VA203-75	Extrusion Resistant	-15 to 400	BLACK	Contact for new business opportunities
VA519-75	Shaft Seals	-15 to 400	BLACK	Contact for new business opportunities
VM330-75	AMS 7276	-15 to 400	BLACK	For AMS 7276 applications
VW076-75	Low Compression Set, UL Listed, alternate for V0884, V1226, VW153, VW305	-15 to 400	BROWN	
VW173-75	Mobile Industrial Applications	-15 to 400	GREEN	
VW340-75	General Purpose	-15 to 400	BROWN	
V7754-80	General Purpose	-15 to 400	BLACK	Contact for new business opportunities
VA090-90	General Purpose, alternate for V0709/VA153	-15 to 400	BLACK	
V0709-90	AMS-R-83248, TY I, CL II, AMS 7259	-15 to 400	BLACK	For AMS 7259 applications
V1411-90	General Purpose	-15 to 400	BLACK	
V1412-90	General Purpose	-15 to 400	BROWN	
VA153-90	General Purpose	-15 to 400	BLACK	Contact for new business opportunities
VA335-90	General Purpose	-15 to 400	BLACK	
VW155-90	General Purpose	-15 to 400	GREEN	Contact for new business opportunities
V1238-95	Extrusion & RGD Resistant, High Pressure CNG, Hydrogen applications	-15 to 400	BLACK	
VA275-95	ISO 23936-2 RGD, Sour Service, Automotive applications	-15 to 400	BLACK	Contact for new business opportunities

Improved Chemical Resistance

V1262-65	Low Swell - Flex Fuel Blends, UL listed, Fuel Handling	-15 to 400	BLACK	Contact for new business opportunities
VW252-65	Low Swell, Gasoline applications	-15 to 400	GREEN	Contact for new business opportunities
VW901-65	Low Swell, Gasoline applications	-15 to 400	GREEN	
VB185-70	Acid Resistant, Steam	-15 to 400	BLACK	Contact for new business opportunities
16327	Automotive Fuel, good permeation resistance, 75 duro	-15 to 400	GREEN	Contact for new business opportunities
V1260-75	Very Chemically Resistant, Viton Extreme" Type	-15 to 400	BLACK	Contact for new business opportunities
V1263-75	Low Swell, Flex Fuel Blends, UL Listed, Fuel Handling	-15 to 400	BLACK	Contact for new business opportunities
VB153-75	Good Compression Set, Fuels	-15 to 400	BLACK	Contact for new business opportunities
VB271-75	Low Set, Coolant Resistant	-15 to 400	BLACK	Contact for new business opportunities
VB282-75	Oil & Coolant Resistant	-15 to 400	BLACK	Contact for new business opportunities
VG162-75	Good Fuel Resistance, "GF" Type	-15 to 400	BLACK	Contact for new business opportunities
V1274-80	USP Class VI, ISO 10993, Low Swell, Steam / Hot Water Resistant	-15 to 400	BLACK	Contact for new business opportunities
VP309-80	Base Resistant, ISO 23936-2 RGD, Sour Service	-10 to 400	BLACK	Contact for new business opportunities
VP316-90	Base Resistant, ISO 23936-2 RGD, Sour Service	-10 to 400	BLACK	Contact for new business opportunities
V1264-90	Low Swell, Flex Fuel Blends, UL Listed, Fuel Handling	-15 to 400	BLACK	Contact for new business opportunities

Improved Low Temperature

VG265-70	Low swell, Low Temp	-25 to 400	BLACK	Contact for new business opportunities
V1163-75	"GFLT" Type, UL Listed, Fuel Handling	-35 to 400	BLACK	Contact for new business opportunities
VG292-75	Engine coolant & biodiesel resistant	-40 to 400	BLACK	Contact for new business opportunities
VG323-75	Engine coolant & biodiesel resistant, alternate for VG292-75	-40 to 400	BLACK	Contact for new business opportunities
VM125-75	"GLT" Type, AMS-R-83485, AMS 7287, ECE R110, Low Set	-40 to 400	BLACK	Contact for new business opportunities
VM128-75	"GLT" Type, AMS-R-83485	-40 to 400	BLACK	Contact for new business opportunities
VM835-75	"GLT" Type, AMS-R-83485, ECE R110	-40 to 400	BLACK	Contact for new business opportunities
VW263-75	"GLT" type, Biodiesel & Coolant resistant	-40 to 400	BROWN	Contact for new business opportunities
VW328-75	"GLT" type, Biodiesel & Coolant resistant, alternate for VW263-75	-40 to 400	BROWN	Contact for new business opportunities

Extreme Low Temperature

VG121-65	Coolant resistant, low closure force	-50 to 400	BROWN	Contact for new business opportunities
VG286-80	Fuel Injectors, Methanol, Biodiesel	-50 to 400	BLACK	Contact for new business opportunities
VG130-75	Coolant resistant, good methanol resistance, High Pressure CNG, Hydrogen	-55 to 400	BLACK	
VX065-75	Extreme Low Temperature, Low Comp Set, AMS 7410, Hydrogen	-65 to 400	BLACK	Contact for new business opportunities
VG109-90	ISO 23936 RGD & Extrusion resistant, High Pressure CNG, Hydrogen	-50 to 400	BLACK	Contact for new business opportunities
VX365-90	Extreme Low Temperature, Low Comp Set, High Pressure CNG, Hydrogen	-65 to 400	BLACK	Contact for new business opportunities

**TFE/PROPYLENE
(AFLAS®) (FPEM)**

V1006-75	AMS 7255, Chemical Processing	+25 to 450	BLACK
VP101-80	General Purpose, Chemical Processing	+25 to 450	BLACK
VP102-80	Low Compression Set	+15 to 450	BLACK
V1041-85	RGD Resistant, General Purpose, NORSOK M710	+15 to 450	BLACK
VP103-95	Extrusion Resistant, Oil & Gas	+25 to 450	BLACK

**HIGH PERFORMANCE
FLUOROELASTOMERS
(HiFluor™)**

HF355-65	MircroE, USP Class VI, Extreme Low Extractables	-15 to 400	TRANSLUCENT	Contact for new business opportunities
HF359-80	MicroE, Resistant to Plasma Etch, Low Metal Ions	-15 to 400	TAN	Contact for new business opportunities

**PERFLUOROELASTOMER
(ULTRA™) (FFKM)**

FF156-75	General Purpose, Oil & Gas, Chemical Processing, Life Science, Low Cost, USP Class VI	5 to 525	BLACK	
FF200-75	Low Compression Set, AMS 7257, FDA, Aerospace, Chemical Processing, MicroE	5 to 608	BLACK	Contact for new business opportunities
FF302-75	MicroE, Etch Resistant, Low Metal Ions	5 to 608	BLACK	Contact for new business opportunities
FF370-75	MicroE, Low Particle Generation, Low Metal Ion content	5 to 608	BLACK	Contact for new business opportunities
FF580-75	Chemical Processing, MicroE, Steam / Amine / Base Resistant, USP Class VI, ISO 23969-2 RGD, Sour Service	5 to 525	BLACK	
V8545-75	Chemical Processing, FDA, General Purpose	5 to 572	BLACK	
V8562-75	MicroE, Plasma Etch Resistant	5 to 572	WHITE	
FF504-80	MicroE, Chemical Processing, Resistant to acids, bases, amines, steam	5 to 525	GREEN	
FF400-85	Oil & Gas, Chemical Processing, Improved Low Temperature	-40 to 525	BLACK	
FF158-90	Oil & Gas, ISO 23936-2 RGD	5 to 525	BLACK	Contact for new business opportunities
FF196-90	ISO 23936-2 RGD, Sour Service	-15 to 525	BLACK	Contact for new business opportunities
FF582-90	Oil & Gas, Chemical Processing, Steam Resistant, Amine / Base Resistant, High Pressure, ISO 23936-2 RGD, Sour Service	5 to 525	BLACK	
V8581-90	MicroE, Plasma Etch Resistant, Low Stiction	5 to 550	WHITE	